

TECHNICAL DATA SHEET

DRICORE™ PRO Concrete Repair Bidirectional Carbon Fiber | Revision Date 09/30/2020

2311 Royal Windsor Drive Unit 2
Mississauga, Ontario, Canada L5J 1K5
P: +1 866 767 6374
E: info@dricore.com

01

01: PRODUCT IDENTIFICATION

2311 Royal Windsor Drive Unit 2
Mississauga, Ontario, Canada L5J 1K5
P: +1 866 767 6374
E: info@dricore.com

(Type-Width-Weight)	Weave Weight
BD-5.5-560	1.03 lb/SY (560 g/m ²)
BD-12-560	1.03 lb/SY (560 g/m ²)
BD-24-560	1.03 lb/SY (560 g/m ²)

Product Name: DRICORE™ PRO Concrete Repair Bidirectional Carbon Fiber

02: DESCRIPTION

DRICORE™ PRO Concrete Repair Bidirectional Carbon Fiber is a high strength, bidirectional carbon fiber fabric. Material is field laminated using DRICORE™ PRO Concrete Repair Saturant-Adhesive Epoxy to form a carbon fiber reinforced polymer (CFRP) used to strengthen structural concrete elements.

03: WHERE TO USE:

Load Increases	<ul style="list-style-type: none">•Increased loading capacity•Installation of heavy machinery in industrial buildings•Vibrating structures•Changes of building utilization•Meeting of changed standards or specifications
Seismic Strengthening	<ul style="list-style-type: none">•Column wrapping•Masonry walls
Damage to Structural Parts	<ul style="list-style-type: none">•Aging of construction material•Vehicle impact•Fire and blast resistance•Prevention of defects caused by earthquakes
Change in Structural System	<ul style="list-style-type: none">•Removal of walls or columns•Removal of slab sections for openings
Design or Construction Defects	<ul style="list-style-type: none">•Insufficient reinforcements•Insufficient structural depth

04: ADVANTAGES

- Used for shear, confinement or structural strengthening
- Flexible, can be wrapped around complex geometries
- High Strength
- Light Weight
- Non-corrosive
- Alkali Resistant
- Low aesthetic impact
- Fiber orientation tailor-made

05: TYPICAL DATA

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Storage Conditions	Store dry at 40° - 95°F (4° - 35°C)
Shelf Life	10 years
Color	Black (red string)
Primary Fiber Direction	Bidirectional

FIBER PROPERTIES			
Property	English	Metric	Test Method
Tensile Strength	710 ksi	4,900 MPa	ISO 10618
Tensile Modulus	36.3 Msi	250 GPa	ISO 10618
Strain	2%	2%	ISO 10618
Density	0.065 lbs / in ³	1.79 g/cm ³	ISO 10119
Nominal Fiber Thickness	0.0275 in.	0.70 mm	



1-866-767-6374 | www.dricore.com

TECHNICAL DATA SHEET

DRICORE™ PRO Concrete Repair Bidirectional Carbon Fiber | Revision Date 09/30/2020

2311 Royal Windsor Drive Unit 2
Mississauga, Ontario, Canada L5J 1K5
P: +1 866 767 6374
E: info@dricore.com

02

06: HOW TO USE: SURFACE PREP

Surface must be clean, sound, and dry. Remove a light layer of concrete from the surface to allow the epoxy to penetrate the substrate (Refer to ICRI 310-2R for additional information). Typical methods include shot blasting or grinding to achieve this open textured surface. Consult the epoxy adhesive data sheets for additional information on surface preparation.

Existing uneven surfaces must be filled with an appropriate repair mortar/hydraulic cement. The adhesive strength of the concrete must be verified after surface preparation by random pull-off testing (ASTM D-4541) at the discretion of the engineer. Minimum tensile strength, 200 psi (1.4 MPa) with concrete substrate failure.

Round all corners to 1/2" radius in certain "contact critical" applications and at the engineers discretion, a thorough cleaning of the substrate using low pressure sand or water blasting may be sufficient.

07: APPLICATION

Application prior to placing the fabric, scarify the concrete surface using dustless grinding system. The fabric may also be manually saturated using your hand, a roller prior or scraper to placement. In either case, installation of this system should be performed only by a trained contractor.

08: TOOLING & FINISHING

Fabric can be cut to appropriate lengths by using scissors. Since the dull or worn cutting implements can damage, weaken or fray the fabric, their use should be avoided.

09: LIMITATIONS

- Design calculations must be made and certified by an independent licensed professional engineer.
- System is a vapor barrier. Concrete should not be fully encapsulated in areas of freeze/thaw.



1-866-767-6374 | www.dricore.com

TECHNICAL DATA SHEET

DRICORE™ PRO Concrete Repair Saturant-Adhesive Epoxy | Revision Date 09/25/2020

2311 Royal Windsor Drive Unit 2
Mississauga, Ontario, Canada L5J 1K5
P: +1 866 767 6374
E: info@dricore.com

01

1. DESCRIPTION

DRICORE™ PRO Concrete Repair Saturant-Adhesive Epoxy is a two-component, 100% solids, moisture-tolerant, low to medium viscosity, high strength, low modulus, multi-purpose liquid epoxy adhesive. It meets the current ASTM C881 and AASHTO M235 Types I, II, IV, & V Grade 3, Classes B & C specifications.

2. WHERE TO USE

DRICORE™ PRO Concrete Repair Saturant-Adhesive Epoxy can be used for wet lay-up structural repairs with carbon fiber reinforced polymer (CFRP), fiberglass reinforced polymer (GFRP) and injections. Use to bond freshly mixed concrete to hardened concrete, to fill voids and cracks in concrete, masonry and other substrates. It can also be injected, used as a binder in epoxy mortar, as an anchoring adhesive, or as a binder for high friction surface treatments (HFST) on concrete, asphalt or other substrates.

3. ADVANTAGES

- High strength/low modulus structural adhesive
- Made in America
- Provides a vapor barrier after curing
- Rapid cure formula
- Convenient 1:1 mix ratio by volume

4. SHELF LIFE / STORAGE

24 month shelf life when stored in unopened containers in dry conditions and stored at 40°F-95°F (4°C-35°C)

5. TECHNICAL DATA

DRICORE™ PRO Concrete Repair Saturant-Adhesive Epoxy Technical Data	
Storage Conditions:	40 °F – 95 °F (5 °C – 35 °C).
Condition material to:	65 °F – 85 °F (18°C – 29 °C) before using.
Mix Ratio	1:1 by volume
Viscosity	2,000 cps @77 °F (25 °C)
Gel Time (60 g mass)	25 minutes
Tack Free Time (73°F or 23°C)	3 to 5 hours
Tensile Properties (ASTM D638), 7 day cure	
Tensile Strength:	2,800 psi (19.3 MPa)
Tensile Elongation:	40%
Bond Strength (ASTM C882)	
2 day cure:	2,000 psi (13.8 MPa)
14 day cure:	2,800 psi (19.3 MPa)
Compressive Properties (ASTM D695), 7 day cure	
Compressive Strength:	5,000 psi (34.5 MPa)
Compressive Modulus:	110,000 psi (760 MPa)
Compressive Strength (ASTM C579)	
3 hour cure:	1,500 psi (10.3 MPa)
24 hour cure:	5,000 psi (34.5 MPa)
Bond Strength (ASTM C1583/ACI 503R)	300 psi (2.0 MPa)
Flexural Strength (ASTM D790)	3,000 psi (20.9 MPa)
Shrinkage on Cure (ASTM D2566)	0.2%
Thermal Compatibility (ASTM C884)	Pass
Heat Deflection Temperature (ASTM D648)	120°F (49°C)
Water Absorption (ASTM D570)	0.2% (24 hr)
Chloride Ion Permeability (AASHTO T277)	0.0 coulomb

*NOTE: Epoxy cure is affected by temperature. Low temperatures will increase cure time, higher temperatures with decrease cure time.

6. MINIMUM CURING TIME

TEMPURATURE	50 °F (10 °C)	60 °F (16 °C)	70 °F (21 °C)	80 °F (26 °C)	90 °F (32 °C)
MINIMUM CURE TIME	10HRS / H	6 HRS / H	4 HRS / H	3 HRS / H	2 HRS / H



1-866-767-6374 | www.Dricore.com

TECHNICAL DATA SHEET

DRICORE™ PRO Concrete Repair Saturant-Adhesive Epoxy | Revision Date 09/25/2020

2311 Royal Windsor Drive Unit 2
Mississauga, Ontario, Canada L5J 1K5
P: +1 866 767 6374
E: info@dricore.com

02

7. APPLICATION TEMPERATURE

Substrate and ambient air temperature between 50°F and 100°F (6°C and 38°C) to be maintained thru the curing period.

8. CONDITION PRODUCT

Condition cartridge and contents to a temperature of 65°F to 85°F (18°C to 29°C) for easier dispensing.

9. LIMITATIONS & WARNINGS

Do not thin. Solvents will prevent proper cure.

10. MANUFACTURER'S PRINTED INSTALLATION INSTRUCTIONS

For complete installation instructions on various applications using DRICORE™ PRO Concrete Repair Saturant-Adhesive Epoxy, visit www.dricore.com or call Dricore for more information at 1-866-767-6374.

11. SURFACE PREPARATION

DRICORE™ PRO Concrete Repair Saturant-Adhesive Epoxy is specially formulated for use as a saturant epoxy for CFRP. New concrete must be a minimum of 28 days old. Surfaces must be clean of all dirt, oil, debris, wax, grease or dust must be removed. Prepare the surface mechanically using a scarifier, sand blast, shot blast, bush hammer or other equipment that will provide a minimum surface profile of CSP3, as defined by ICRI 310.2R. A roughened surface that exposes the aggregate and/or pores of the substrate is imperative for good adhesion.

12. CLEAN UP

Clean tools and equipment with Mighty Wipes by Dricore, a biodegradable formula that removes and neutralizes the epoxy. Do not allow epoxy to harden on equipment as cured material can only be removed mechanically.

13. SAFETY

Please refer to the SDS for DRICORE™ PRO Concrete Repair Saturant-Adhesive Epoxy published on our website, www.dricore.com or call Dricore for more information at 1-866-767-6374. This TDS sheet is not intended to list all Safety and Health Requirements necessary for the installation of these products. All Health and Safety Requirements required by OSHA shall be followed.

14. WARRANTY

Dricore warrants to the Buyer that this product is in good quality and conforms to the manufacturer's specifications in force on the date of manufacturer when used in accordance with the Installation Instructions and when stored as directed in the technical literature.

Manufacturer cannot warrant or guarantee any particular method of use, performance or application under any particular condition and Buyer is responsible for determining the suitability of intended purpose and assumes all risks therein. Dricore shall not be liable for any injury, loss, cost of labor or consequential damages either directly, indirectly or incidentally, arising out of the use or misuse of any product sold by Dricore or another distributor. If the product is proven to be in non-conformance, the Buyers sole remedy shall be a refund of the purchase price or replacement of product.



1-866-767-6374 | www.Dricore.com