

Thermal Properties



**Tested in Accordance with
ASTM C518-10**

Result: Thermal Resistance
of RSI-2.82 [R-16] at 107.95
mm [4.25 in]

Vapour Barrier



**Tested in Accordance with
ASTM E96/E96M-10**

Result: Average Water
Vapour Permeance of 26
ng/PaSm²

Flame Spread Panel



**Tested in Accordance with
CAN/ULC-S102-10**

Result: Flame Spread = 4.9
Smoke Development = 10.8

Flame Spread Corner



**Tested in Accordance with
CAN/ULC-S102-10**

Result: Flame Spread = 4.9
Smoke Development = 10.8